

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-085775

(43)Date of publication of application : 02.04.1996

(51)Int.Cl. C09D171/02
C09D 4/00
C09D 4/06
C09D 5/00
C09D 5/00
// C09D163/00

(21)Application number : 06-248647

(71)Applicant : TOAGOSEI CO LTD

(22)Date of filing : 16.09.1994

(72)Inventor : NIWA MAKOTO
OTA HIROYUKI

(54) COMPOSITION FOR PRODUCING PRECOATED STEEL SHEET

(57)Abstract:

PURPOSE: To obtain a composition for a precoated steel sheet having a high curing rate and giving a cured film excellent in hardness, impact resistance, adhesion to steel sheet and bendability by mixing a compound having oxetane rings with a cationic photopolymerization initiator.

CONSTITUTION: This composition is obtained by mixing a compound (A) having 1-4 oxetane rings with an epoxy compound (B), a compound (C) having a vinyl ether group or a compound (D) having a (meth)acryloyl group (D) as an optional component and a radical photopolymerization initiator in a weight ratio (B to D)/(A to D) of (5-95)/100, and adding 0.1-20wt.%, based on the total of components A to C, a cationic photopolymerization initiator. The radical photopolymerization initiator is used in an amount of 0.01-20wt.% based on component D. This composition is applied to the surface of a steel sheet and cured by irradiation with an actinic radiation to obtain a precoated steel sheet.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]